

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

Report Information

Submitting Organisation : 00100847 : Macsim Australia|New Zealand Pty Ltd
Account : 144432 : Macsim Australia|New Zealand Pty Ltd
AWQC Reference : 144432-2021-CSR-2 : Prod Test: 53TRGT (Translucent) MF50 Trans - Roof & Gutter
Project Reference : PT-4643
Product Designation : MF50 Roof and Gutter
Composition of Product : Silicone (Translucent).
Product Manufacturer : Hangzhou, CHINA.
Use of Product : In-Line/Silicone for Tanks, Guttering and Roofing.
Sample Selection: As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018
Extracts : Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.
Project Completion Date : 10-Sep-2021
Project Comment : Product sample was received on the 11-May-2021 and testing commenced 08-Jun-2021.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

Summary of Results

APPENDIX/CLAUSE	RESULTS
C – Taste	Passed at an exposure of 2500 mm ² per Litre.
D – Appearance	Passed at an exposure of 2500 mm ² per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 2500 mm ² per Litre.
F – Cytotoxic Activity	Passed at an exposure of 2500 mm ² per Litre.
G – Mutagenic Activity	Passed at an exposure of 2500 mm ² per Litre.
H – Metals	Passed at an exposure of 2500 mm ² per Litre.
6.8 – Organic Compounds	Passed at an exposure of 2500 mm ² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2120c & APHA 2130b
E	TO014-03	APHA 4500 O G
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

Summary Comment :

The sealant was applied and cured for seven days at 20°C prior to testing.



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

CLAUSE 6.2

Taste

Sample Description

The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Taste (Appendix C)

Test Information

Scaling Factor

Not applied.

Results

Not detected (sample and controls).

Evaluation

The product passed the requirements of clause 6.2 when tested at an exposure of 2500 mm² per Litre.

Number of Samples

2.

Test Comment

The 24 hour extracts were not analysed in this test.

m glasson.
Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

CLAUSE 6.3

Appearance

Sample Description

The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Appearance (Appendix D)

Scaling Factor

Not applied.

Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation

The product passed the requirements of clause 6.3 when tested at an exposure of 2500 mm² per Litre.

Number of Samples

1.

Test Comment

Not applicable.

Melissa Phillips
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports: 319641.

Report ID : 319732

CLAUSE 6.4

Growth of Aquatic Micro-organisms

Sample Description

The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of test water.

Test Method

Growth of Aquatic Micro-organisms (Appendix E)

Inoculum

The volume of the inoculum was 100 mL

Scaling Factor

Not applied.

Results

Mean Dissolved Oxygen	Control	7.6 mg/L
Mean Dissolved Oxygen Difference	Positive Reference	5.3 mg/L
	Negative Reference	<0.1 mg/L
	Test	1.60 mg/L

Evaluation

The product passed the requirements of clause 6.4 when tested at an exposure of 2500 mm² per Litre.

Number of Samples

1.

Test Comment

Not applicable.

Ben Drew
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

CLAUSE 6.5

Cytotoxic Activity

Sample Description

The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Cytotoxic Activity (Appendix F)

Scaling Factor

Not applied.

Results

Non-cytotoxic (sample and controls).

Evaluation

The product passed the requirements of clause 6.5 when tested at an exposure of 2500 mm² per Litre.

Number of Samples

1.

Test Comment

The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.


Mira Maric

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports: 319641.

Report ID : 319732

CLAUSE 6.6

Mutagenic Activity

Sample Description The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Mutagenic Activity (Appendix G)

Scaling Factor Not applied.

Results

	<u>Bacteria Strain</u>	<u>Number of Revertants per Plate</u>			
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	24, 30, 22	31, 31, 31	3658, 3576, 3345	<u>NPD</u> (20µg)
Mean ± Standard deviation		25.3 ± 4.2	31.0 ± 0.0	3526.3 ± 162.3	
	+	37, 27, 33	27, 33, 33	3616, 3615, 3620	<u>2-AF</u> (20µg)
Mean ± Standard deviation		32.3 ± 5.0	31.0 ± 3.5	3617.0 ± 2.6	
<i>Salmonella typhimurium</i> TA102	-	425, 466, 469	427, 420, 409	2232, 2247, 2173	<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		453.3 ± 24.6	418.7 ± 9.1	2217.3 ± 39.1	
	+	545, 504, 456	462, 428, 491	1896, 2215, 2479	
Mean ± Standard deviation		501.7 ± 44.5	460.3 ± 31.5	2196.7 ± 291.9	

Comments S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment The differences in the mean number of revertants between the blank and test extracts do not exceed two standard deviations; accordingly there is no evidence of a mutagenic response.

Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

CLAUSE 6.7

Metals

Sample Description

The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Metals (Appendix H)

Scaling Factor

Not applied.

Method of Analysis

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
----------------	----------------------------	---------------	----------------	----------------	---------------------

Final Extract

Aluminium	0.001	<0.001	0.006	0.006	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.01
Barium	0.0005	<0.0005	<0.0005	<0.0005	0.7
Boron	0.020	<0.020	0.038	0.028	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	<0.0001	<0.0001	<0.0001	2.0
Iron	0.0005	<0.0005	<0.0005	<0.0005	0.3
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Manganese	0.0001	<0.0001	<0.0001	<0.0001	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation


The product passed the requirements of clause 6.7 when tested at an exposure of 2500 mm² per Litre.

Number of Samples

1.

Test Comment

Not applicable.



Dzung Bui

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of one panel (coated on a single side) with dimensions 25 mm x 100 mm providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

Scaling Factor Not applied.

Results

Organic Compound

Nitrosamines	Blank	Test	Max Allowed
	µg/L	µg/L	
!External Lab Report No.	ES2122722	ES2122722	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

Organic Compound

Phenols	Blank	Test	Max Allowed
	µg/L	µg/L	
!External Lab Report No.	ES2122722	ES2122722	
2,4,5-trichlorophenol	<1.0	<1.0	
2,4,6-trichlorophenol	<1.0	<1.0	20 µg/L
2,4-dichlorophenol	<1.0	<1.0	200 µg/L
2,4-dimethylphenol	<1.0	<1.0	
2,6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	
phenol	<1.0	<1.0	9 µg/L

Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

Organic Compound

Phthalate Esters

	Blank	Test	Max Allowed
	µg/L	µg/L	
!External Lab Report No.	ES2122722	ES2122722	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

Organic Compound

Polycyclic Aromatic Hydrocarbons

	Blank	Test	Max Allowed
	µg/L	µg/L	
!External Lab Report No.	ES2122722	ES2122722	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

Organic Compound

Volatile Organic Compounds GCMS

	Blank µg/L	Test µg/L	Max Allowed
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	<1	<1	60 µg/L
Bromoform	<1	<1	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	<1	<1	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	<1	<1	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

This report supersedes the following issued reports:

319641.

Report ID : 319732

Organic Compound

Volatile Organic Compounds GCMS

	Blank µg/L	Test µg/L	Max Allowed
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	<1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	<3	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	<4	<4	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation

The product passed the requirements of clause 6.8 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment

Subcontracted testing conducted by ALS, Environmental Division, NATA accreditation no. 825 site no. 10911 and ALS Scoresby, NATA accreditation no. 992, site no. 989

A handwritten signature in black ink, appearing to read "Qiong Huang".

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

